

# Technical Data

## Jotafloor Sealer



### Product description

Jotafloor Sealer is a transparent two-pack epoxy sealer/primer exhibiting excellent penetration properties to ensure good adhesion between Jotafloor products and most masonry surfaces.

---

### Recommended use

As a sealer/primer for subsequent Jotafloor products or for use independently as a dust binder for concrete floors.

---

### Film thickness and spreading rate

	Minimum	Maximum	Typical
Film thickness, dry (µm)	30	50	40
Film thickness, wet (µm)	80	130	100
Theoretical spreading rate (m <sup>2</sup> /l)	12,5	7,7	10

### Comments

Substrate porosity and profile will affect practical coverage rates.

---

### Physical properties

Colour	Transparent
Solids (vol %)*	40 ± 2
Flash point	25°C ± 2 (Setaflash)
Gloss	Glossy
Water resistance	Very good
Solvent resistance	Excellent
Chemical resistance	Excellent Check chemical resistance values in Jotafloor chemical resistance chart.
Flexibility	Good

\*Measured according to ISO 3233:1998 (E)

---

### Surface preparation

All concrete damaged by exposure to chemicals, contaminated by any substance or unsound in any way, shall be removed to expose sound concrete.

#### Coated surfaces

Clean, dry and undamaged compatible primer. Contact your local Jotun office for more information.

#### Other surfaces

Concrete surface preparation by using dust free captive blasting units, grinding equipment, sand blasting or high pressure water jetting is critical to achieving the right surface profile prior to paint application. Contact your local Jotun office for more information.

The coating may be used on other substrates. Please contact your local Jotun office for more information.

---

## Condition during application

The temperature of the substrate should be minimum 10°C and at least 3°C above the dew point of the air, temperature and relative humidity measured in the vicinity of the substrate. Good ventilation is usually required in confined areas to ensure proper drying. The moisture content in the concrete should not exceed 4 % (by weight). The coating should not be exposed to oil, chemicals or mechanical stress until fully cured.

---

## Application methods

<b>Spray</b>	Use airless spray or conventional spray
<b>Brush</b>	Recommended for stripe coating and small areas, care must be taken to achieve the specified dry film thickness.
<b>Roller</b>	May be used. However when using roller application care must be taken to apply sufficient material in order to achieve the specified dry film thickness.

---

## Application data

<b>Mixing ratio (volume)</b>	4 parts Comp. A (base) to be mixed thoroughly with 1 part Comp. B (curing agent). NO PART MIXING
<b>Mixing</b>	½ hour prior to use.
<b>Pot life (23°C)</b>	8 hours (reduced at higher temp.)
<b>Thinner/Cleaner</b>	Jotun Thinner No. 17
<b>Guiding data airless spray</b>	
<b>Pressure at nozzle</b>	15 MPa (150 kp/cm <sup>2</sup> 2100 psi)
<b>Nozzle tip</b>	0.46 - 0.58 mm (0.018-0.023")
<b>Spray angle</b>	40-80°
<b>Filter</b>	Check to ensure that filters are clean

---

## Drying time

Drying times are generally related to air circulation, temperature, film thickness and number of coats, and will be affected correspondingly. The figures given in the table are typical with:

- \* Good ventilation (Outdoor exposure or free circulation of air)
- \* Typical film thickness
- \* One coat on top of inert substrate

<b>Substrate temperature</b>	<b>10°C</b>	<b>23°C</b>	<b>40°C</b>
<b>Surface dry</b>	2 h	1 h	0.5 h
<b>Through dry</b>	14 h	6,5 h	3 h
<b>Cured</b>	14 d	7 d	2 d
<b>Dry to recoat, minimum</b>	8 h	4 h	1,5 h

1. The surface should be free from chalking and contamination prior to application. Best intercoat adhesion occurs when the subsequent coat is applied before the preceding coat has cured.

The given data must be considered as guidelines only. The actual drying time/times before recoating may be shorter or longer, depending on film thickness, ventilation, humidity, underlying paint system, requirement for early handling and mechanical strength etc. A complete system can be described on a system sheet, where all parameters and special conditions could be included.

---

## Typical paint system

As dust binder:

**Jotafloor Sealer**

**Nominal**

For coloured finish:

**Jotafloor Sealer**

**1 x 40 µm**

**(Dry Film Thickness)**

Jotafloor Topcoat

2 x 50 µm

(Dry Film Thickness)

or

**Jotafloor Sealer**

**1 - 2 x 40 µm**

**(Dry Film Thickness)**

Jotafloor Coating

1 x 300 µm

(Dry Film Thickness)

or

**Jotafloor Sealer**

**1 - 2 x 40 µm**

**(Dry Film Thickness)**

Jotafloor SL Universal

1 x 2000 - 4000 µm

(Dry Film Thickness)

**Note:** Thickness of the finished system will vary depending on use of the finished floor. Consult your local Jotun Office for advice.

**Other systems may be specified, depending on area of use**

---

## Storage

The product must be stored in accordance with national regulations. Storage conditions are to keep the containers in a dry, cool, well ventilated space and away from source of heat and ignition. Containers must be kept tightly closed.

---

## Handling

Handle with care. Stir well before use.

---

## Packing size

16 l Comp. A (base) and 4 l Comp. B (curing agent)

4 l Comp. A (base) and 1 l Comp. B (curing agent)

Packing may vary from country to country according to local requirements.

---

## Health and safety

Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.

**For detailed information on the health and safety hazards and precautions for use of this product, we refer to the Material Safety Data Sheet.**

---

## DISCLAIMER

*The information in this data sheet is given to the best of our knowledge based on laboratory testing and practical experience. However, as the product is often used under conditions beyond our control, we cannot guarantee anything but the quality of the product itself. We reserve the right to change the given data without notice.*

Jotun is a World Wide company with factories, sales offices and stocks in more than 50 countries. For your nearest local Jotun address please contact the nearest regional office or visit our website at [www.jotun.com](http://www.jotun.com)

ISSUED 6 DECEMBER 2007 BY JOTUN  
THIS DATA SHEET SUPERSEDES THOSE PREVIOUSLY ISSUED