

Technical Data

Primastic Universal



Product description

Primastic Universal is a two-pack, surface-tolerant, high solids epoxy mastic coating. Available with different hardeners for varying substrate temperatures, Standard (Std) and Wintergrade (WG).

Recommended use

Anticorrosive primer for steel structures above and below water, also on steel where blast cleaning may not be possible.

Film thickness and spreading rate

Std Comp. B	Minimum	Maximum	Typical
Film thickness, dry (μm)	100	250	125
Film thickness, wet (μm)	135	330	165
Theoretical spreading rate (m^2/l)	7,5	3	6
WG Comp. B	Minimum	Maximum	Typical
Film thickness, dry (μm)	100	250	125
Film thickness, wet (μm)	145	360	180
Theoretical spreading rate (m^2/l)	7	2,8	5,6

Physical properties

Colour	Aluminium, Aluminium Red toned
Solids (vol %)*	75 \pm 2 Std Comp. B 70 \pm 2 WG Comp. B
Flash point	Std Comp. B: 35°C \pm 2 (Setaflash) WG Comp. B: 31°C \pm 2 (Setaflash)
VOC	Std Comp. B 2,67 lbs/gal (320 gms/ltr) USA-EPA Method 24 210 gms/ltr UK-PG6/23(97). Appendix 3 WG Comp. B 230 gms/ltr UK-PG6/23(97). Appendix 3
Gloss	Semigloss
Gloss retention	Fair
Water resistance	Very good
Abrasion resistance	Very good
Solvent resistance	Good
Chemical resistance	Good
Flexibility	Good

*Measured according to ISO 3233:1998 (E)

Surface preparation

All surfaces should be clean, dry and free from contamination. The surface should be assessed and treated in accordance with ISO 8504.

Bare steel

Cleanliness: Power tool cleaning to min. St 2, mill scale free (ISO 8501-1:2007). Improved surface treatment (blast cleaning to Sa 2½) will improve the performance.

Shoppripped steel

Clean, dry and undamaged approved shopprimer.

Coated surfaces

Clean, dry and undamaged compatible primer. Contact your local Jotun office for more information. For maintenance UHPWJ to WJ2 (NACE No.5/SSPC-SP 12) or Power tool cleaning to min. St 2 for rusted areas

Other surfaces

The coating may be used on other substrates. Please contact your local Jotun office for more information.

Condition during application

The temperature of the substrate should be minimum +10°C (Std) (-5°C in WG) and at least 3°C above the dew point of the air, temperature and relative humidity measured in the vicinity of the substrate. Good ventilation is required in confined areas to ensure proper drying. The coating should not be exposed to oil, chemicals or mechanical stress until cured.

Application methods

Spray	Use airless spray
Brush	Recommended for stripe coating and small areas, care must be taken to achieve the specified dry film thickness.
Roller	May be used for small areas but not recommended for first primer coat, however when using roller application care must be taken to apply sufficient material in order to achieve the specified dry film thickness.

Application data

Mixing ratio (volume)	Std Comp. B: 5:1 WG Comp. B: 4:1
Mixing	5 parts Comp. A (base) to be mixed thoroughly with 1 part Primastic Universal, Std Comp.B (curing agent). 4 parts Comp. A (base) to be mixed thoroughly with 1 part Primastic Universal, WG Comp. B (curing agent).
Induction time	10 minutes.
Pot life (23°C)	Std Comp. B: 2 hours WG Comp. B: 1 hour
Thinner/Cleaner	Jotun Thinner No. 17

Guiding data airless spray

Pressure at nozzle	15 MPa (150 kp/cm ² , 2100 psi.).
Nozzle tip	0.53 - 0.79 mm (0.021 - 0.031")
Spray angle	40-80°
Filter	Check to ensure that the filters are clean.

Note

- * The temperature of the mixture of base and curing agent is recommended to be at least 15°C, otherwise extra solvent may be required to obtain correct viscosity.
- * Too much solvent results in lower sag resistance and slower cure.
- * If extra solvent is necessary, this should be added after mixing of the two components.

Drying time

Drying times are generally related to air circulation, temperature, film thickness and number of coats, and will be affected correspondingly. The figures given in the table are typical with:

- * Good ventilation (Outdoor exposure or free circulation of air)
- * Typical film thickness
- * One coat on top of inert substrate

Std Comp. B

Substrate temperature	10°C	23°C	40°C
Surface dry	8 h	4 h	2 h
Through dry	24 h	10 h	4 h
Cured	14 d	7 d	2 d
Dry to recoat, minimum	24 h	10 h	4 h
Dry to recoat, maximum ¹			

WG Comp. B

Substrate temperature	-5°C	0°C	5°C	10°C	23°C
Surface dry	24 h	18 h	12 h	6 h	2,5 h
Through dry	48 h	26 h	18 h	12 h	5 h
Cured	21 d	14 d	7 d	3 d	2 d
Dry to recoat, minimum	48 h	26 h	18 h	12 h	5 h
Dry to recoat, maximum ¹					

1. Provided the surface is free from chalking and other contamination prior to application, there is normally no overcoating time limit. Best intercoat adhesion occurs, however, when the subsequent coat is applied before preceding coat has cured. If the coating has been exposed to direct sunlight for some time, special attention must be paid to surface cleaning and mattening/removal of the surface layer in order to obtain good adhesion.

The given data must be considered as guidelines only. The actual drying time/times before recoating may be shorter or longer, depending on film thickness, ventilation, humidity, underlying paint system, requirement for early handling and mechanical strength etc. A complete system can be described on a system sheet, where all parameters and special conditions could be included.

Typical paint system

Primastic Universal	2 x 125 µm	(Dry Film Thickness)
Hardtop AS/XP	1 x 50 µm	(Dry Film Thickness)

Other systems may be specified, depending on area of use

Storage

The product must be stored in accordance with national regulations. Storage conditions are to keep the containers in a dry, cool, well ventilated space and away from source of heat and ignition. Containers must be kept tightly closed.

Handling

Handle with care. Stir well before use.

Packing size

16 litres Comp. A (base) in a 20 litre container and 3.2 litres Primastic Universal, Std Comp. B (curing agent) in a 5 litre container.

16 litres Comp. A (base) in a 20 litre container and 4 litres Primastic Universal, WG Comp. B (curing agent) in a 5 litre container.

Health and safety

Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.

For detailed information on the health and safety hazards and precautions for use of this product, we refer to the Material Safety Data Sheet.

DISCLAIMER

The information in this data sheet is given to the best of our knowledge based on laboratory testing and practical experience. However, as the product is often used under conditions beyond our control, we cannot guarantee anything but the quality of the product itself. We reserve the right to change the given data without notice.

Jotun is a World Wide company with factories, sales offices and stocks in more than 50 countries. For your nearest local Jotun address please contact the nearest regional office or visit our website at www.jotun.com

ISSUED 19 DECEMBER 2007 BY JOTUN
THIS DATA SHEET SUPERSEDES THOSE PREVIOUSLY ISSUED