

# Technical Data

## SeaLion Tiecoat



### Product description

SeaLion Tiecoat is a three-pack silicone elastomeric tiecoat. IMO Anti-fouling System Convention compliant (AFS/CONF/26).

---

### Recommended use

To promote adhesion of SeaLion Topcoat. Constitutes a part of the SeaLion fouling release coating (FRC) system.

---

### Film thickness and spreading rate

	Minimum	Maximum	Typical
Film thickness, dry ( $\mu\text{m}$ )			90
Film thickness, wet ( $\mu\text{m}$ )			150
Theoretical spreading rate ( $\text{m}^2/\text{l}$ )			6,4

---

### Physical properties

Colour	White
Solids (vol %)*	58 $\pm$ 2
Flash point	24°C $\pm$ 2
VOC	3,59 lbs/gal (430 gms/ltr) USA-EPA Method 24 406 gms/ltr UK-PG6/23(97). Appendix 3

\*Measured according to ISO 3233:1998 (E)

---

### Surface preparation

#### Coated surfaces

To be applied on a clean, dry Safeguard Universal ES. The primer must be fresh, not applied more than three days prior to the SeaLion Tiecoat application.

#### Other surfaces

The coating may be used on other substrates. Please contact your local Jotun office for more information.

---

### Condition during application

The temperature of the substrate must be minimum 5°C and at least 3°C above the dew point of the air, temperature and relative humidity measured in the vicinity of the substrate. The air temperature must be minimum 5°C. Good ventilation is usually required in confined areas to ensure proper drying. Relative humidity during application and drying should be minimum 30%.

---

## Application methods

<b>Spray</b>	Use airless spray
<b>Other</b>	Care should be taken to avoid overspray onto other coated areas.

---

## Application data

<b>Mixing ratio (volume)</b>	16,7 litres Comp. A (base) to be mixed thoroughly with 0,6 litres Comp. B (Curing agent). Then add 0,9 litre comp. C (catalyst) and mix thoroughly again.
<b>Pot life (23°C)</b>	1 hours
	0,5 hours (40°C)
<b>Thinner/Cleaner</b>	Do not thin.
<b>Cleaner</b>	Jotun Thinner No. 7
<b>Guiding data airless spray</b>	
<b>Pressure at nozzle</b>	15 MPa (211 kp/cm <sup>2</sup> , 3000 psi).
<b>Nozzle tip</b>	0,38 mm - 0,53 mm (0,015" - 0,021")
<b>Filter</b>	Check to ensure that filters are clean
<b>Note</b>	Sagging may occur if application procedure and specification are not followed.

---

## Drying time

Drying times are generally related to air circulation, temperature, film thickness and number of coats, and will be affected correspondingly. The figures given in the table are typical with:

- \* Good ventilation (Outdoor exposure or free circulation of air)
- \* Typical film thickness
- \* One coat on top of inert substrate

<b>Substrate temperature</b>	<b>5°C</b>	<b>10°C</b>	<b>15°C</b>	<b>23°C</b>	<b>40°C</b>
<b>Surface dry</b>	17 h	15 h	12 h	6 h	3 h
<b>Dry to recoat, minimum</b>	24 h	24 h	24 h	15 h	6 h
<b>Dry to recoat, maximum</b>	4 d	4 d	4 d	4 d	4 d

The given data must be considered as guidelines only. The actual drying time/times before recoating may be shorter or longer, depending on film thickness, ventilation, humidity, underlying paint system, requirement for early handling and mechanical strength etc. A complete system can be described on a system sheet, where all parameters and special conditions could be included.

---

## Recommended type of primer:

SeaLion Tiecoat MUST only be applied on Safeguard Universal ES.  
Application on any other substrate can give adverse effects on adhesion.

The SeaLion FRC system constitutes of SeaLion Tiecoat and SeaLion Topcoat. SeaLion Tiecoat is applied to anticorrosive layer as adhesion promotion layer for SeaLion Topcoat.

Muki EPS (optional)	1 x 30 µm	(Dry Film Thickness)
Anticorrosive primer system suitable for purpose	1 x 200 µm	(Dry Film Thickness)
Safeguard Universal ES	1 x 100 µm	(Dry Film Thickness)
<b>SeaLion Tiecoat</b>	<b>1 x 90 µm</b>	<b>(Dry Film Thickness)</b>
SeaLion Topcoat	1 x 135 µm	(Dry Film Thickness)

**Overcoating with itself (SeaLion Tiecoat) is not recommended.**

---

## Storage

The product must be stored in accordance with national regulations. Storage conditions are to keep the containers in a dry, cool, well ventilated space and away from source of heat and ignition. Containers must be kept tightly closed.

---

## Handling

Handle with care. Stir well before use.

---

## Packing size

16,7 litre Comp. A (base) in a 20 litre container, 0,6 litre Comp. B in a 0,75 litre container and 0,9 litre Comp. C in a 1 litre container.

---

## Health and safety

Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.

**For detailed information on the health and safety hazards and precautions for use of this product, we refer to the Material Safety Data Sheet.**

---

## DISCLAIMER

*The information in this data sheet is given to the best of our knowledge based on laboratory testing and practical experience. However, as the product is often used under conditions beyond our control, we cannot guarantee anything but the quality of the product itself. We reserve the right to change the given data without notice.*

Jotun is a World Wide company with factories, sales offices and stocks in more than 50 countries. For your nearest local Jotun address please contact the nearest regional office or visit our website at [www.jotun.com](http://www.jotun.com)

ISSUED 6 DECEMBER 2007 BY JOTUN  
THIS DATA SHEET SUPERSEDES THOSE PREVIOUSLY ISSUED